

DIN 1748.1

			Rm	RP	A5	A10	Brinell
			N/mm2	N/mm2	% min	% min	
AlMgSi0,5	F13	3.3206.51	130	65	15	13	45
	F22	71	215	160	12	10	70
	F25	72	245	195	19	8	75
AlmgSi0,7	F26	3.3210.7	260	215	8	6	85
	F27	71	270	225	8	6	90
AlMgSi0,8	F28	3.2316.71	275	200	10	8	80
AlMgSi1	F21	3.2315.51	205	110	14	12	65
	F28	71	275	200	12	10	80
	F31	72	310	260	10	8	95
AlMgSiCu	F18	3.3211.51	180	110	16	14	55
	F26	71	260	240	8	6	90
AlMg3	F18	3.3535.08	180	80	14	12	45